

Structural Basis for the Anomalously Low Spontaneous Polarisation Values of the Polar Phase of $\text{Sr}_{1-x}\text{Ca}_x\text{TiO}_3$ ($x=0.02, 0.04$): Evidence for a Ferrielectric Ordering

Sanjay Kumar Mishra

Solid State Physics Division, Bhabha Atomic Research Center, Trombay, Mumbai 400 085, India

Dhananjai Pandey*

School of Materials Science and Technology, Institute of Technology Varanasi-221005, India

(Dated: November 23, 2009)

Full pattern Le-Bail refinement using x-ray powder diffraction profiles of $\text{Sr}_{1-x}\text{Ca}_x\text{TiO}_3$ for $x=0.02, 0.04$ in the temperature range 12 to 300 K reveals anomalies in the unit cell parameters at 170, 225 K due to an antiferrodistortive (cubic to tetragonal $I4/mcm$) phase transition and at $\sim 32, \sim 34\text{K}$ due to a transition to a polar phase (tetragonal $I4/mcm$ to orthorhombic $Ic2m$), respectively. The lower transition temperatures obtained by us are in excellent agreement with those reported on the basis of the dielectric studies by Bednorz and Muller,¹⁰ who attributed these to ferroelectric transition. Rietveld analysis of the diffraction profiles of the polar phase reveals off-centre displacements of both $\text{Sr}^{2+}/\text{Ca}^{2+}$ and Ti^{4+} ions in the X-Y plane along $\langle 110 \rangle$ pseudocubic directions, in agreement with the experimentally reported direction of easy polarization by Bednorz and Muller, but the resulting dipole moments are shown to be ferrielectrically coupled in the neighbouring (001) planes along the [001] direction leading to anomalously low values of the spontaneous polarization at 12 K.

PACS numbers: 77.84.Dy; 77.80.-e;

SrTiO_3 has been the paradigm of structural phase transition studies.¹ It is also one of the most common ingredients of BaTiO_3 -based ceramic capacitors.² The room temperature cubic perovskite structure of SrTiO_3 (space group $Pm\bar{3}m$) transforms to a tetragonal phase in the $I4/mcm$ space group below 105 K due to the freezing of one of the triply degenerate R_{25} modes in which the adjacent octahedra rotate about one of the cubic $\langle 100 \rangle$ directions in an anti-phase manner.³ Although the tetragonal phase is reported to be stable down to the lowest temperature,⁴ its dielectric constant gradually increases on cooling and becomes nearly two orders of magnitude greater at $\sim 4\text{K}$ below which it levels off. While the increasing value of the dielectric constant at low temperatures is linked to a zone centre soft mode,¹ its saturation below 4 K has been attributed to quantum fluctuations (i.e., zero point vibrations) of the lattice which stabilize the paraelectric state.⁵ Ca^{2+} substitution not only increases the antiferrodistortive phase transition temperature^{6,7} but also suppresses the quantum fluctuations, as revealed by the appearance of a peak in the temperature variation of the dielectric constant. In fact, the quantum fluctuations can be suppressed by several ways, such as by the application of external stress,⁸ electric field⁹ and suitable chemical substitutions like Ca^{2+} , Ba^{2+} , Pb^{2+} at the Sr^{2+} site and oxygen isotope (O^{18}) at the O^{2-} sites.^{10,11} It has been shown by Bednorz and Muller¹⁰ that above a critical Ca^{2+} concentration of $x_c = 0.0018$, XY type 'ferroelectricity' is stabilized in SrTiO_3 . The ferroelectric transition temperature (T_c) rises with Ca^{2+} concentration (x) upto $x = 0.016$ according to the relationship $T_c \sim (x - x_c)^{0.5}$ as expected for quantum transitions.¹⁰ In the composition range $0.016 < x < 0.12$, the transition tempera-

ture is nearly composition independent ($T_c \sim 35\text{K}$) and the variation of dielectric constant with temperature is increasingly more smeared out as the Ca^{2+} content increases. This smearing out of the transition has been attributed by Bednorz and Muller¹⁰ to the formation of mesoscopic 'ferroelectric' domains caused by the random fields induced by some of the Ca^{2+} occupying Ti^{4+} sites, thereby forming $\text{Ca}^{2+} - V_o$ (V_o is oxygen vacancy) dipoles. Ranjan et al¹² have argued that this smearing could as well be the result of a frustration caused by the competing ferroelectric and antiferroelectric instabilities for these compositions, since the nature of the phase transition in $\text{Sr}_{1-x}\text{Ca}_x\text{TiO}_3$ (SCT) changes from 'ferroelectric' for low Ca^{2+} doping levels to antiferroelectric for high Ca^{2+} concentrations with $x > 0.12$. Raman scattering studies¹³ reveal the presence of both the antiferroelectric and ferroelectric modes for $x=0.12$ in support of the frustration model.

For Ca^{2+} concentrations $x_c < x < 0.12$, the dielectric constant of SCT in the 'ferroelectric' state decreases with increasing x but its value ($> 10^4$) remains an order of magnitude larger than that of the conventional ferroelectrics like BaTiO_3 .¹⁰ On the otherhand, the measured saturation polarization values ($\sim 0.5\mu\text{C}/\text{cm}^2$) are anomalously low^{14,15} in the 'ferroelectric' phase as compared to that in BaTiO_3 , which is $\sim 25\mu\text{C}/\text{cm}^2$. There is no satisfactory explanation for such a low value of saturation polarization ($\sim 0.5\mu\text{C}/\text{cm}^2$) in a 'ferroelectric' phase with extremely high dielectric constant. The present work seeks to provide a structural basis for this low value of spontaneous polarization.

No attempt has so far been made to examine the structure of the 'ferroelectric' phase of SCT for $x_c > 0.0018$ using diffraction techniques. In the present work, we have

investigated the phase transitions in SCT for $x=0.02$ and 0.04 (SCT02 and SCT04) in the temperature range 12 to 300 K by Le-Bail and Rietveld techniques of x-ray powder diffraction, with a view to capture the structural signatures of the antiferrodistortive and 'ferroelectric' transitions. Our results suggest that the anomalously low spontaneous polarization value of SCT is linked with the 'ferrielectric' nature of the hitherto regarded 'XY-ferroelectric' phase of SCT. The calculated spontaneous polarization values, obtained using the Rietveld refined atomic positions and Born-effective charges, as given in Ref.¹⁶, are found to be in excellent agreement with the values reported by Bianchi et al¹⁴ and Mitsui and Westphal.¹⁵

SCT02 and SCT04 powders were prepared by solid-state thermochemical reaction in the appropriate stoichiometric mixtures of $SrCO_3$, $CaCO_3$ and TiO_2 at 1423 K for 6 h in alumina crucibles. The calcined powders were sintered at 1573 K for 6 h. The sintered pellets were crushed to fine powder and subsequently annealed at 823 K for 12 h for removing the strain induced, if any, during the crushing process before using them for diffraction studies. Temperature dependent powder x-ray diffraction studies in the 12 to 300 K range were carried out using a 18 kW Rigaku (RINT 2000/ PC series) rotating anode based high resolution x-ray powder diffractometer operating in the Bragg-Brentano focusing geometry. The diffractometer is fitted with a He- closed cycle refrigerator based low temperature attachment and also a curved crystal monochromator in the diffraction beam. Data were collected in the continuous scan mode at a scan speed of 1 degree per minute and step interval of 0.01 degree. The package 'Fullprof'¹⁷ was used for Le-Bail and Rietveld analysis of the x-ray diffraction data.

For pure $SrTiO_3$, the cubic to tetragonal antiferrodistortive phase transition is accompanied with the doubling of the elementary perovskite cell leading to characteristic splitting of main perovskite peaks along with the appearance of superlattice reflections.⁴ The relationship between the tetragonal cell parameters (a_t, b_t, c_t) with the elementary perovskite cell parameters (a_p, b_p, c_p) is as follows: $a_t = b_t \approx \sqrt{2}a_p, c_t \approx 2c_p$. The Miller indices of the main perovskite and superlattice reflections of the tetragonal phase with $a^0a^0c^-$ tilt system are all even (eee) and all odd (ooo) integers, respectively, when indexed with respect to a pseudocubic $2a_p \times 2b_p \times 2c_p$ unit cell (see Glazer¹⁸ for details). Figs. 1 (a) and (b) depict the evolution of the 311 superlattice and 800 perovskite reflections as a function of temperature for SCT02 and SCT04, respectively. It is evident from these figures that the 800 profile is a doublet at low temperatures. It is also evident from this figure that the intensity of the superlattice reflection, as also the splitting of the 008 peak, disappears at high temperatures, as expected for the high temperature phase. In order to determine the phase transition temperatures, we analysed the powder diffraction data in the 2θ range of 20 to 110 deg at various temperatures by Le-Bail technique¹⁷ using the $I4/mcm$ space group. The




FIG. 1: Evolution of the XRD profile of the 311 superlattice and 800 perovskite reflections of (a) $Sr_{0.98}Ca_{0.02}TiO_3$ (SCT02) and (b) $Sr_{0.96}Ca_{0.04}TiO_3$ (SCT04). The indices are with respect to a doubled pseudocubic perovskite cell.

variations of the equivalent elementary perovskite cell parameters with temperature, as obtained from the refined cell parameters of the tetragonal phase, are plotted in Fig. 2. It is evident from this figure that the cubic to tetragonal transition occurs around $T_c = 170$ and 225 K for $x=0.02$ and 0.04 , respectively. Combining these two transition temperatures with the previously reported values for $x = 0.0, ^{19}0.007, ^60.01, 0.06$ and 0.12^7 one gets a dT_c/dx as $34.83K/mole$ for $x < 0.06$ and $12.54K/mole$ for $x > 0.06$ showing a kink corresponding to a change of slope (dT_c/dx) at $x \sim 0.06$ in the T_c versus 'x' plot, as noted by Mishra et al earlier⁷ but missed in a recent report.²⁰

Although the XRD profiles shown in Fig. 1 do not depict any qualitative change in the 'ferroelectric phase' (i.e., below 35 K), the refined tetragonal cell parameters show anomalies around 30 K in Fig.2. Since the transition temperatures reported in the literature for SCT02 and SCT04 are around $\sim 32K$,¹⁰ the anomalies in the cell parameters at $\sim 30K$ are evidently linked with the phase transition from the tetragonal paraelectric phase to the lower temperature 'ferroelectric' phase. The centrosymmetric $I4/mcm$ space group of the paraelectric tetragonal phase cannot represent the structure of the ferroelectric phase. The onset of ferroelectric polarization transforms under $Pm\bar{3}m$ as the components of the Γ_4^- irreducible representation (IR). Anti-phase tilting of oxygen octahedra transforms under $Pm\bar{3}m$ as the components of the R_4^+ IR.²¹ Using the software package "ISOTROPY 2000"²¹ to couple Γ_4^- and R_4^+ and IRs,




FIG. 2: Evolution of the equivalent elementary perovskite cell parameters of $Sr_{0.98}Ca_{0.02}TiO_3$ (SCT02) and $Sr_{0.96}Ca_{0.04}TiO_3$ (SCT04) as a function of temperature showing the phase transition to the cubic phase around 170 K and 225 K, marked with arrows. The anomaly ~ 32 K, linked with the transition to the polar phase, is marked with arrows.

we obtained many space groups. Since the paraelectric phase of SCT is tetragonal ($I4/mcm$), we impose the constraint that the 'ferroelectric space' group is a subgroup of $I4/mcm$. This constraint reduced the number of possible space groups for the ferroelectric phase to two, namely: $I4cm$ and $Ic2m$ (bca setting of $Ima2$). The Raman scattering studies on SCT with $x = 0.007$ ⁶ have shown that the E_g mode is split into two lines in the 'ferroelectric phase' and hence the tetragonal $I4cm$ space group, for which E_g mode should have remained a singlet, cannot represent the ferroelectric phase. Thus, the orthorhombic space group $Ic2m$ is the mostly likely space group of the ferroelectric (polar) phase of SCT for which E_g mode will indeed be a doublet. The equivalent elementary perovskite cell parameters obtained at various temperatures by Le-Bail analysis of the full diffraction profiles in the 2θ range 20 to 120 degrees using the $Ic2m$ space group are depicted in Figs. 3(a) and (b) for SCT02 and SCT04, respectively. The cell parameters (A_o, B_o, C_o) of the orthorhombic $Ic2m$ phase are related to the elementary perovskite cell parameters (a_p, b_p, c_p) as: $A_o \approx \sqrt{2}a_p, B_o \approx \sqrt{2}b_p$ and $C_o = 2c_p$. It is evident from this figure that the a_p lattice parameter of the tetragonal paraelectric phase splits below ~ 32 K into a_p and b_p of the orthorhombic phase, in good agreement with the transition temperature ($T_c \sim 32$ K) at which the dielectric peak is observed.¹⁰

Having identified the most plausible space group for the polar phase, we carried out Rietveld analysis of the 12 K XRD data in the 2θ range 20 to 110 degree for SCT02 and SCT04 using the $Ic2m$ (bca setting of $Ima2$) space group. In this space group, Sr/ Ca occupy the 4b Wyckoff site at $(0 \pm u, 0 \pm v, 0.25)$ and the Ti occupies 4a Wyckoff site at $(0, 0.5 \pm v, 0.5)$. There




FIG. 3: Evolution of the equivalent elementary perovskite cell parameters of $Sr_{0.98}Ca_{0.02}TiO_3$ (SCT02) and $Sr_{0.96}Ca_{0.04}TiO_3$ (SCT04) as a function of temperature showing the orthorhombic splitting of the a parameter of the tetragonal phase below ~ 32 K.

are two types of oxygen atoms, O(1) at 4b Wyckoff site at $(0 \pm u, 0.5 \pm v, 0.5)$ and O(2) at 8c site at $(0.25 \pm u, 0.75 \pm v, 0 \pm w)$. Pseudo-Voigt function was used to define the profile shapes while background was estimated by linear interpolation between fixed values. Except for the occupancy parameters of atoms, which were fixed at their nominal compositions, all other parameters were refined. Table 1 depicts the refined structural parameters for the ferroelectric phase of SCT02 and SCT04, respectively.

Fig. 4 depicts schematically the ionic displacements in the orthorhombic ferroelectric phase of SCT02/04 with respect to the ideal positions in the paraelectric phase. The crystal structure of ferroelectric phase consists of the stacking of TiO, Sr/CaO, TiO and Sr/CaO layers at $z = 0, 1/4, 1/2$ and $3/4$ of the unit cell of ferroelectric phase, as shown in Fig. 4. All the ions in these layers are displaced with respect to their ideal positions in cubic perovskite structure. In the layers at $z = 1/4$ and $3/4$, the Sr^{2+}/Ca^{2+} and O^{2-} ions have component displacements both along $\pm[100]$ and $[010]$ directions of the orthorhombic cell. However, the component displacements along $\pm[100]$ in the $z = 1/4$ and $z = 3/4$ planes cancel out leaving net effective displacement only along the $[010]$ direction of the orthorhombic phase. Similarly, for the layers at $z = 0$ and $1/2$, the net displacements of Ti^{4+} and O^{2-} ions are along the $[0\bar{1}0]$ direction of orthorhombic ferroelectric phase. Thus the direction of polarization in the TiO as well as Sr/CaO layers is along $\pm[010]$ direction of the orthorhombic phase. This is in agreement with the observation of Bednorz and Muller¹⁰ that the $\langle 110 \rangle$ pseudo-cubic direction, which becomes $\langle 010 \rangle$ in the orthorhombic cell, is the easy direction of polarization. However, results of our refinements reveal fer-

TABLE I: Refined structural parameters of the ferrielectric phase of SCT02 and SCT04 at 12 K using orthorhombic space group $Ic2m$.

Atoms	$Sr_{0.98}Ca_{0.02}TiO_3(SCT02)$				$Sr_{0.98}Ca_{0.04}TiO_3(SCT04)$			
	x	y	z	B ($\text{\AA}$) ²	x	y	z	B ($\text{\AA}$) ²
Sr/Ca	0.0018(9)	0.0091(7)	0.25	0.67(7)	0.0028(2)	0.0083(5)	0.25	0.89(5)
Ti	0.00	0.4894(7)	0.50	0.008(5)	0.00	0.4891(9)	0.50	0.011(7)
O1	-0.023(3)	0.552(7)	0.25	0.052(1)	-0.021(6)	0.5598(2)	0.25	0.24(7)
O2	0.267(3)	0.7148(7)	0.001(2)	0.67(7)	0.2588(2)	7101(7)	0.003(4)	0.70(7)
Lattice Parameters ($\text{\AA}$)								
	A=5.5073(3)	B=5.5066(2)	C=7.7977(1)		A=5.4979(3)		B=5.4997(2)	C=7.7908(1)
	$R_p=11.90$	$R_{wp}=18.73$	$R_e=12.97$	$\chi^2 = 2.08$	$R_p=8.87$	$R_{wp}=13.0$	$R_e=9.36$	$\chi^2 = 1.94$




FIG. 4: (color online) Schematic diagram showing the ionic displacements in the orthorhombic ferrielectric phase of $Sr_{0.98}Ca_{0.02}TiO_3(SCT02)$ as layer wise and net displacements of ions from its ideal position respectively. Sr^{2+}/Ca^{2+} , Ti^{4+} and O^{2-} ions are represented by filled circle with green, red and blue color, respectively. The arrows indicate only the directions of displacement component along the unit cell axes and not the magnitudes.

rielectric coupling of the dipole moments residing in the neighbouring (001) layers, in contrast to the suggestions of Bednorz and Muller¹⁰ for ferroelectric order, since the dipole moments are along the $[0\bar{1}0]$ and $[010]$ directions in the alternate (001) layers stacked in the $[001]$ direc-

tion. Using the Born effective charges given in Ref¹⁶ for $Sr/Ca(q = 2.56C)$, $Ti(q = 7.26C)$, $O(-3.2733C)$ along-with the refined positional coordinates given in Table 1, we obtain a spontaneous polarization of $0.98\mu C/cm^2$ and $1.17\mu C/cm^2$ for $x = 0.02$ and 0.04 , respectively. These values are in excellent agreement with the values reported by Bianchi et al¹⁴ and Mitsui and Westphal¹⁵ on the basis of hysteresis loop measurements. Thus the extremely low value of spontaneous polarization, in spite of the very high dielectric constant, of SCT02 and SCT04 is due to the partial cancellation of the dipole moments as a result of the ferrielectric coupling of the dipoles in the $[001]$ direction of the orthorhombic phase.

To summaries, we have shown that the orthorhombic distortion of the lattice of $Sr_{1-x}Ca_xTiO_3$ ($x=0.02, 0.04$) below 35 K is clearly revealed through the Le-Bail analysis of the powder x-ray diffraction profiles. Using symmetry arguments in conjunction with Raman scattering results from literature, we have proposed the $Ic2m$ space group for the low temperature polar phase. This phase is not ferroelectric in nature, as hitherto believed, but ferrielectric. The dipole moments in the neighbouring (001) planes are coupled ferrielectrically in the $[001]$ direction. The value of spontaneous polarization calculated using the Born-effective charges and the refined positional coordinates obtained by Rietveld technique are in excellent agreement with experimental values reported in the literature.

-
- * Electronic address: dpandey@bhu.ac.in, dpandey.bhu@yahoo.co.in
- ¹ M. E. Lines and A. M. Glass, Principles and Applications of Ferroelectrics and Related Materials(Clarendon , Oxford, 1977), A. D. Bruce and R. A. Cowley, Advances in Physics, **29**, 219 (1980).
- ² R.C. Buchman "Ceramic Materials for Electronics: Processing Properties and Application" (Marcel Dekker, New York, 1991).
- ³ G.Shirane and Y. Yamada, Phys. Rev. **177**, 858 (1979).
- ⁴ J. M. Kiat, and T Roisnel J. Phys. Condens. Matter, **8**, 3471 (1996).
- ⁵ K A Muller, and H. Burkard, Phys. Rev. B, **19**, 3593 (1979).
- ⁶ J. Bianchi et al., J. Phys. Condens.Matter, **6**, 1229 (1994).
- ⁷ M. E., Guzhva et al., Phys. Solid State, **39**, 625 (1997); M.C. Gallardo et al., J. Phys.: Condens. Matter, **15**, 91 (2003). S.K. Mishra et al., J.Solid State Chem. **178**, 2846 (2005).
- ⁸ H. Uwe and T. Sakudo, Phys. Soc. Jpn. **23**, 546 (1967).
- ⁹ P.A. Fleury, and J. M. Worlock Phys. Rev. B, **174**, 613 (1968).
- ¹⁰ J. G. Bednorz, and K. A. Muller, Phys. Rev. Lett. **52**, 2289 (1984).
- ¹¹ M. E., Guzhva et al., Phys. Solid State, **39**, 618 (1997a); V. V. Lemanov et al., Phys. Solid State, **39**, 628 (1997); M. Itoh et al.,Phys. Rev. Lett., **82**, 3540 (1999).

- ¹² R. Ranjan et al., Phys. Rev. Lett., **84**, 3726 (2000); R. Ranjan, and D. Pandey J.Phys.: Condens. Matter bf 13, 4251 (2001).
- ¹³ R. Ouillon et al., J. Phys. Condens. Matter, **14**, 2079 (2002).
- ¹⁴ U. Bianchi et al., Phys. Rev.B, **51**, 8737 (1995).
- ¹⁵ T. Mitsui and W. B. Westphal, Phys. Rev., **124**, 1354 (1961).
- ¹⁶ Ph. Ghosez et al., Phys. Rev. B **58**, 6224(1998).
- ¹⁷ J. Rodriguez-Carvajal, FULLPROF, Laboratory Leon Brillouin (CEA-CNRS) CEA/Saclay, 91191 Gif sur Yvette Cedex, France, (2006).
- ¹⁸ A. M. Glazer Acta. Cryst., B28, 3384 (1972); ibid Acta Cryst., **A31**, 756 (1975).
- ¹⁹ K. A. Muller et al., Phys. Rev. Lett., **21**, 814 (1968).
- ²⁰ M. A. Carpenter et al., J.Phys. Condens. Matter, **18**, 10725 (2006).
- ²¹ D.M., Hatch, and , H.T., Stokes Phys. Rev. B **35**, 8509(1987); H.T. Stokes, and D. M. Hatch, ISOTROPY software and documentation is available over the internet at www.physics.byu.edu/stokes/isotropy.html.